102.10 Lead Base Alloys (disk and powder forms) [150 g units (unless otherwise noted)]

Technical Contact: john.sieber@nist.gov

PLEASE NOTE: The tables are presented to facilitate comparisons among a family of materials to help customers select the best SRM for their needs. For specific values and uncertainties, the certificate is the only official source.

SRM		Description	Elemental Composition (mass fraction, in %, unless noted by an asterisk (*) for mg/kg)										
Powder	Disk		Pb	Cu	Ni	As	Sn	Sb	Bi	Ag	Fe	Co	In
1129		Solder 63Sn-37Pb (200 g)		0.16	0.010	0.055	62.7	0.13	0.13	0.075			
127b	1131	Solder 40Sn-60Pb		0.011	0.012	0.01	39.3	0.43	0.06	0.01			
53e	1132	Bearing Metal (Pb-Sb-Sn)		0.054	0.003	0.057	5.84	10.26	0.052		<0.001		
1727		Anode Tin (blockform) (30x30x30 mm)	33.26*	(4)*	(3)*	(<100)*		(40)*	(8)*		(20)*	(2)*	(20)*

*Values in parentheses are given for information only.